#### IN THE CLAIMS

1. (Currently Amended) A multilayer article comprising:

(i)-a coating layer comprising a block copolyestercarbonate comprising structural units derived from at least one 1,3-dihydroxybenzene and at least one an aromatic dicarboxylic acid, (ii)

a second layer comprising a polymer comprising carbonate structural units, (iii)

an adhesive layer comprising an adhesive material and a resinous copolymer, wherein the adhesive material comprises a polyurethane, wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated diene, and wherein the resinous copolymer is compatible with the adhesive material, and

(iv) a substrate layer comprising at-least one material selected from the group consisting of a thermoplastic resin, a cured thermoset resin, a metal, a ceramic, a glass, and a cellulosic material, and mixtures thereof, wherein the coating layer is in contiguous contact with the second layer, and the adhesive layer is in contiguous contact with the second layer and the substrate layer.

- 2. (Currently Amended) The article of claim 1 wherein the coating layer comprises at-least one 1,3-dihydroxybenzene selected from the group consisting of unsubstituted resorcinol, 2-methyl resorcinol, and mixtures thereof.
- 3. (Original) The article of claim 2 wherein the 1,3-dihydroxybenzene is unsubstituted resorcinol.
- 4. (Original) The article of claim 1 wherein the aromatic dicarboxylic acid is selected from the group consisting of isophthalic acid, terephthalic acid, naphthalene-2,6-dicarboxylic acid, and mixtures thereof.
- 5. (Original) The article of claim 4 wherein the aromatic dicarboxylic acid is a mixture of isophthalic acid and terephthalic acid.

4

- 6. (Original) The article of claim 5 wherein the ratio of isophthalic-derived structural units to terephthalic-derived structural units is about 0.25-4.0:1.
- 7. (Original) The article of claim 5 wherein the ratio of isophthalic-derived structural units to terephthalic-derived structural units is about 0.40-2.5:1.
- 8. (Original) The article of claim 1 wherein the copolyesterearbonate comprises about 10% to about 99% by weight arylate blocks.
- 9. (Original) The article of claim 1 wherein the copolyestercarbonate comprises about 60% to about 98% by weight arylate blocks.
- 10. (Original) The article of claim 1 wherein the carbonate portion of the copolyesterearbonate comprises structural units derived from bisphenol A.
- 11. (Original) The article of claim 1 wherein the second layer comprises a bisphenol A polycarbonate.
- 12. (Currently Amended) The article of claim 1 wherein the second layer further comprises at-least-one colorant selected from the group consisting of dyes, pigments, metal flakes, and glass flakes, and mixtures thereof.
- 13. (Currently Amended) The article of claim 1 wherein the adhesive layer comprises at-least-one polyurethane comprising structural units derived from at-least-one polyol selected from the group consisting of polyether polyols, polyester polyols, polytetramethylene ether glycol, hexamethylene glycol, and-polyols based on polybutadiene, and mixtures thereof.
- 14. (Original) The article of claim 13 wherein the polyurethane comprises structural units derived from methylene diphenyl diisocyanate or methylene biscyclohexyl diisocyanate.
- 15. (Original) The article of claim 1 wherein the polyurethane comprises an aliphatic polyurethane film.

(Currently Amended) The article of claim 1 wherein the substrate layer 22. comprises at least-one thermoplastic resin selected from the group consisting of condensation polymers, polycarbonates, aromatic polycarbonates, bisphenol A polycarbonate, polyacetals, polyarylene ethers, polyphonylene ethers, polyprylene-sulfides, polyphonylene sulfides, polyimides, polyamideimides, polyetherimides, polyetherketones, polyaryletherketones, polyetheretherketones, polyetherketoneketones, polyamides, copolyamides, polyesters, licuid crystalline-polyesters, polyetheresters, polyetheramides, polyesteramides, polyestercarbonates; poly(alkylene-diearboxylates),-poly(ethylene-terephthalate),-poly(1,4-butylene-terephthalate), poly(trimethylene—terephthalate),---poly(ethylene—naphthalate), poly(butylene—naphthalate); poly(cyclohexanedimethanol——lerephthalate),——poly(cyclohexanedimethanol-co-ethylene terephthalate), --poly(1,4-cyclohoxanedimethyl-1,4-cyclohoxanedicarboxylate); --polyarylates, -a polyarylate -- comprising structural units derived from bisphenol-A, terephthalic acid, and isophilialic-acid; addition-polymers, homo- and copolymeric aliphatic olefin and functionalized olefin polymers, polyethylene, polypropylene, thermoplastic polyolefin, ethylene-propylene copolymer, poly(vinyl - chloride), poly(vinyl ehleride-co-vinylidene chloride), poly(vinyl fluoride), poly(vinylidene fluoride), poly(vinyl-acetate), poly(vinyl-alechol), poly(vinyl-butyral), poly(aerylonitrile), -acrylie--polymers, -poly(meth)acrylamides, -polyalkyl- (meth)aerylates, poly(methyl-methacrylate) polymers of alkenylaromatic compounds, polystyrenes, syndiotactic polystyrene;-aerylonitrile-butadiene-styrene-(ABS);-and-aerylonitrile-styrene-acrylate-(ASA) copolymers; and blends thereof.

## 23 - 26. (Cancelled)

- 27. (Currently Amended) The article of claim I wherein thicknesses of layers are: othe coating layer has a thickness of about 2-2,500 microns; a-the second layer has a thickness of about 2-2,500 microns; and the an-adhesive layer has a thickness of about 8-2,500 microns.
  - 28. (Cancelled)

# 29. (Currently Amended) A multilayer article comprising:

-(i)-a coating layer comprising a block copolyestercarbonate comprising structural units derived from unsubstituted resorcinol, a mixture of isophthalic acid and terephthalic acid, and bisphenol A;-(ii)

a second layer comprising a bisphenol A polycarbonate optionally containing at least one colorant, (iii)

an adhesive layer comprising a resinous copolymer and comprising an adhesive material selected from the group consisting of a polyurethane; an aliphatic polyurethane film; thermoplastic polyurethane; and a block copolymer comprising a thermoplastic polyurethane block and at least one block comprising structural units derived from styrene; and a blend-of-(a) a block-copolymer-comprising a thermoplastic polyurethane block and at least-one-block comprising-structural-units-derived-from styrene, and (b)-a-resinous copolymer-comprising structural-units-derived-from styrene; and (iv), wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated diene, wherein the resinous copolymer is compatible with the adhesive material, and

a substrate layer selected from the group consisting of a thermoplastic resin, a cured thermoset resin, a metal, a ceramic, a glass, and a cellulosic material;

wherein the coating layer is in contiguous contact with the second layer, and the adhesive layer is in contiguous contact with the second layer and the substrate layer; and wherein the multilayer article exhibits a ninety-degree peel force of at least 700 Newtons per meter.

## 30. (Currently Amended) A film assembly comprising:

-(i)-a coating layer comprising a block copolyesterearbonate comprising structural units derived from at least-one 1,3-dihydroxybenzene and-at-least-one an aromatic dicarboxylic acid, (ii)

a second layer comprising a polymer comprising carbonate structural units, and (iii)

an adhesive layer comprising an adhesive material and a resinous copolymer, wherein the adhesive material comprises a polymethane, wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated diene, and wherein the resinous copolymer is compatible with the adhesive material.

# 31. (Currently Amended) A film assembly comprising: (i)

a coating layer comprising a block copolyestercarbonate comprising structural units derived from unsubstituted resorcinol, a mixture of isophthalic acid and terephthalic acid, and bisphenol A; (ii)

a second layer comprising a bisphenol A polycarbonate optionally containing at least one colorant, and (iii)

an adhesive layer comprising a resinous copolymer and comprising an adhesive material selected from the group consisting of a polyurethane; an aliphatic polyurethane film; thermoplastic polyurethane; and a block copolymer comprising a thermoplastic polyurethane block and at least one block comprising structural units derived from styrene; and a blend-of (a) a block-copolymer-comprising a thermoplastic polyurethane block-and at least-one block comprising structural units derived from styrene, and (b) a resinous copolymer comprising structural units derived from styrene,

wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated dieue, wherein the resinous copolymer is compatible with the adhesive material.

- 35. (Currently Amended) The method of claim 32 wherein the coating layer comprises at-least-one 1,3-dihydroxybenzene selected from the group consisting of unsubstituted resorcinol, 2-methyl resorcinol, and mixtures thereof.
- 36. (Original) The method of claim 35 wherein the 1,3-dihydroxybenzene is unsubstituted resorcinel.
- 37. (Original) The method of claim 32 wherein the aromatic dicarboxylic acid is selected from the group consisting of isophthalic acid, terephthalic acid, naphthalene-2,6-dicarboxylic acid, and mixtures thereof.
- 38. (Original) The method of claim 37 wherein the aromatic dicarboxylic acid is a mixture of isophthalic acid and terephthalic acid.
- 39. (Original) The method of claim 38 wherein the ratio of isophthalic-derived structural units to terephthalic-derived structural units is about 0.25-4.0:1.
- 40. (Original) The method of claim 39 wherein the ratio of isophthalic-derived structural units to terephthalic-derived structural units is about 0.40-2.5: 1.
- 41. (Original) The method of claim 32 wherein the copolyestercarbonate comprises about 10% to about 99% by weight arylate blocks.
- 42. (Original) The method of claim 32 wherein the copolyestercarbonate comprises about 60% to about 98% by weight arylate blocks.
- 43. (Original) The method of claim 32 wherein the carbonate portion of the copolyesterearbonate comprises structural units derived from bisphenol A.
- 44. (Original) The method of claim 32 wherein the second layer comprises a bisphenol A polycarbonate.
- 45. (Currently Amended) The method of claim 32 wherein the second layer further comprises at-least-one colorant selected from the group consisting of dyes, pigments, metal flakes, and glass flakes.

- 46. (Currently Amended) The method of claim 32 wherein the adhesive—layer comprises at least—one—polyurethane comprisesing structural units derived from at least—one polyol selected from the group consisting of polyether polyols, polyester polyols, polytetramethylene ether glycol, hexamethylene glycol, and polyols based on polybutadiene.
- 47. (Original) The method of claim 46 wherein the polyurethane comprises structural units derived from methylene diphenyl diisocyanate or methylene biscyclohexyl diisocyanate.
- 48. (Original) The method of claim 32 wherein the polyurethane comprises an aliphatic polyurethane film.
- 49. (Currently Amended) The method of claim 32 wherein the adhesive layer comprises a block copolymer comprising a thermoplastic polymethane-block and at least one block comprising structural units derived from styrene, and a block comprising the polymethane, wherein the polymethane is thermoplastic polymethane.
- 50. (Original) The method of claim 49 wherein the block comprising structural units derived from styrene comprises a hydrogenated styrene-diene block.
  - 51. (Cancelled)
- 52. (Currently Amended) The method of claim—51—49 wherein the alkenyl aromatic compound comprises additional resinous-material-is a copolymer comprising-structural units derived from styrene.
  - 53. (Cancelled)
- 54. (Currently Amended) The method of claim 53 wherein the multilayer-article exhibits a ninety-degree peel force of at least 1750 Newtons per meter.

(Currently Amended) The method of claim 32 wherein the substrate layer 55. comprises at-least-one thermoplastic resin selected from the group consisting of conclusation polymers, polycarbonates, aromatic polycarbonates, bisphenol A polycarbonate, polyacetals, polyarylene ethers, polyphenylene ethers, polyarylene sulfides, polyphenylene sulfides, polyimides, polyamideimides, polyetherimides, polyetherketones, polyetherketones, polyetheretherketones, polyetherketoneketones, polyamides, copolyamides, polyesters, liquid crystalline-polyesters,-polyetheresters, polyetheramides,-polyesteramides, polyestercarbonates; poly(alkylene dicarboxylates), poly(ethylene-terephthalate), poly(1;4-butylene-terephthalate), poly(trimethylene-terephthalate), -poly(ethylene-naphthalate), -poly(butylene-naphthalate), poly(cyclohexanedimethanol——terephthalate), poly(cyclohexanedimethanol-co-ethylene tereplathalate),—poly(-1,4-cyclohexanedianethyl-1,4-cyclohexanedicarboxylate);—polyarylates.—a polyarylate -- comprising structural-units derived from bisphonol A, terephthalic-acid, and isophthalic acid; addition polymers; homo- and copolymeric aliphatic olefin and functionalized olefin polymers, polyethylene, polypropylene, thermoplastic polyolefin, ethylene propylene copolymer, -- poly(vinyl--chloride), -- poly(vinyl--chloride-co-vinylidene--chloride), -- poly(vinyl fluoride), poly(vinylidene fluoride), poly(vinyl-acetate), poly(vinyl-alcohol), poly(vinyl-butyral), poly(nerylonileile), nerylic polyniers, poly(meth)acrylamides, polyalkyl (meth)acrylates, poly(methyl-methacrylate) polymers of alkenylaromatic compounds, polystyrenes, syndiotaclic polystyrene; acrylonitrile butadiene styreno-(ABS), and acrylonitrile styrene acrylate-(ASA) copolymers; and blends thereof.

#### 56 - 59. (Cancelled)

60. (Currently Amended) The method of claim 32 wherein thicknesses of layers are: n-the\_coating layer has a thickness of about 2-2,500 microns; and an-the adhesive layer has a thickness of about 8-2,500 microns.

#### 61. (Cancelled)

62. (New) The article of claim 22 wherein the thermoplastic resin is selected from the group consisting of polyethylene, polypropylene, thermoplastic polyolefin, ethylene-propylene copolymer, and blends thereof.

- 63. (New) The article of claim 22 wherein the thermoplastic resin comprises thermoplastic polyolefin.
  - 64. (New) The method of claim 32,

wherein the block copolyestercarbonate further comprises structural units derived from bisphenol A,

wherein the 1,3-dihydroxybenzene comprises unsubstituted resorcinol,

wherein the aromatic dicarboxylic acid comprises a mixture of isophthalic acid and terephthalic acid,

wherein the polymer is a bisphenol A polycarbonate,

wherein the adhesive material is selected from the group consisting of an aliphatic polyurethane film; a thermoplastic polyurethane; and a block copolymer comprising a thermoplastic polyurethane block and at least one block comprising structural units derived from styrene, and

wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated diene, and wherein the resinous copolymer is compatible with the adhesive material.

- 65. (New) The method of claim 55 wherein the thermoplastic resin is selected from the group consisting of polyethylene, polypropylene, thermoplastic polyolefin, ethylene-propylene copolymer, and blends thereof.
- 66. (New) The article of claim 55 wherein the thermoplastic resin comprises thermoplastic polyolefin.

# 67. (New) A multilayer article comprising:

a coating layer comprising a block copolyestercarbonate comprising structural units derived from a 1,3-dihydroxybenzene and an aromatic dicarboxylic acid,

an adhesive layer comprising an adhesive material and a resinous copolymer, wherein the adhesive material comprises a polyurethane, wherein the resinous copolymer comprises structural units derived from an alkenyl aromatic compound and a conjugated diene, and wherein the resinous copolymer is compatible with the adhesive material, and

a substrate layer comprising a substrate material selected from the group consisting of homo- and copolymeric aliphatic olefin and functionalized olefin polymers,

wherein the adhesive layer is disposed between the coating layer and the substrate.

- 68. (New) The article of claim 67 wherein the substrate material is selected from the group consisting of polyethylene, polypropylene, thermoplastic polyolefin, ethylene-propylene copolymer, and blends thereof.
- 69. (New) The article of claim 67 wherein the substrate material comprises thermoplastic polyolefin.
- 70. (New) The article of claim 67 wherein the resinous copolymer comprises an elastomeric polystyrene-b-poly(isoprene)-b-polystyrene block copolymer.
- 71. (New) The article of claim 70 wherein the elastomeric polystyrene-b-poly(isoprene)-b-polystyrene block copolymer is a block copolymer comprising polystyrene end blocks and a vinyl-bonded, polyisoprene-rich middle block.
- 72. (New) The article of claim 70 wherein the elastomeric polystyrene-b-poly(isoprene)-b-polystyrene block copolymer is hydrogenated.

# 73. (New) A multilayer article comprising:

a coating layer comprising a block copolyestercarbonate comprising structural units derived from a 1,3-dihydroxybenzene and an aromatic dicarboxylic acid,

an adhesive layer comprising a block copolymer comprising a polyurethane block comprising a structural unit derived from a polyurethane and a styrene block comprising a structural unit derived from styrene, and

a substrate layer comprising a material selected from the group consisting of a thermoplastic resin, a cured thermoset resin, a metal, a ceramic, a glass, a cellulosic material, and mixtures thereof,

wherein the adhesive layer is disposed between the coating layer and the substrate,

- 74. (New) The article of claim 73 wherein the substrate material is selected from the group consisting of polyethylene, polypropylene, thermoplastic polyolefin, ethylene-propylene copolymer, polystyrene, polyarylene other, polyphenylene ether, and blends thereof.
- 75. (New) The article of claim 73 wherein the substrate material comprises thermoplastic polyolefin.

# This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

# **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

BLACK BORDERS

IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT OR DRAWING

BLURRED OR ILLEGIBLE TEXT OR DRAWING

SKEWED/SLANTED IMAGES

COLOR OR BLACK AND WHITE PHOTOGRAPHS

GRAY SCALE DOCUMENTS

LINES OR MARKS ON ORIGINAL DOCUMENT

REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

# IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.